

# SHOWOOD

## TEST REPORT

**REPORT NUMBER**

170821003SHF-BP-9

**ISSUE DATE**

2017-12-14


**PAGES**

4

**DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10a

© 2017 INTERTEK



## Test Report

Issue Date: 2017-12-14

Intertek Report No. 170821003SHF-BP-9

Applicant: SHOWOOD

Applicant Address: 186 KARAMANILI AV, 13678, ACHARNAI ATHENS GREECE

Manufacturer: SHOWOOD IKE

Manufacturer

Address:

Performance testing

**SUBJECT:** WPC decking

Dear Sir,

This test report represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

**TEST METHODS AND STANDARDS**

Refer to the next following Pages.

SAMPLE ID	MODEL	SPECIFICATION
S170821003SHF.009	ET017	146x23mm

SAMPLE RECEIEVED: 2017-09-04

TESTED FROM: 2017-09-04 TO 2017-12-14

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

## Test Report

Issue Date: 2017-12-14

Intertek Report No. 170821003SHF-BP-9

**Test Items, Method and Results:**

Test Items	Test Method	Test Results
Resistance to artificial weathering	ASTM D7032-17 Section 4.6 ASTM G154-16 cycle 1	Exposure time (h): 2000 $\Delta L^* =$ -1.43 $\Delta a^* =$ 0.06 $\Delta b^* =$ -0.13 $\Delta E^* =$ 1.43 Grey Sale= 4

Tested sample photo:



# Test Report

Issue Date: 2017-12-14


Intertek Report No. 170821003SHF-BP-9

**APPENDIX: SAMPLE RECEIVED PHOTO**

Front view




Back view




Section view

**REPORT AUTHORIZED**

When signed with physical or electronic signature, the contents of this report have been prepared and approved per Intertek's quality process in accordance with ISO 17025.

  
Sun Sun  Sally Xie   
Name: Sun Sun Name: Sally Xie  
Title: Approver Title: Reviewer

Tod Qian   
Name: Tod Qian  
Title: Project Engineer

**Revision:**

NO.	DATE	CHANGES	AUTHOR	REVIEWER
170821003SHF-BP-9	2017-12-14	First issue	Tod Qian	Sally Xie